

CLAIMS

RECEIVED
CENTRAL FAX CENTER
AUG 16 2006

We claim:

1. (Withdrawn) A bioactive sol-gel solution, comprising:
a biocompatible polymer,
a gelable inorganic base material, and
at least one calcium and phosphorous molecular species
2. (Withdrawn) The solution of claim 1, wherein said base material comprises at least one alkoxysilane
3. (Withdrawn) The solution of claim 1, wherein said base material comprises at least one non-alkoxysilane alkoxide selected from the group consisting of aluminates, titanates and borates.
4. (Withdrawn) The solution of claim 1, wherein said polymer comprises at least one selected from the group consisting of polyvinylpyrrolidone (PVP), polyethyleneimine (PEI), polycarboxymethylcellulose (PCMC), polyethyleneglycol (PEG), polypropylene oxide (PPO), polyvinylalcohol (PVA), polyacrylic acid (PAA), polymethylacrylic acid (PMAA) polystyrene sulfonic acid (PSSA), and gelatin
5. (Withdrawn) The solution of claim 1, wherein a pH of said solution is from 1 to 7.
6. (Withdrawn) The solution of claim 5, wherein said pH is from 1.2 to 2.
7. (Withdrawn) The solution of claim 1, wherein a viscosity of said solution at 25 C is from 1.5 Pa sec. to 6.0 Pa sec.

{WP325900:1}

8. (Withdrawn) The solution of claim 1, wherein said solution is stable for at least 30 days at 25 C.

9. (Withdrawn) The solution of claim 1, further comprising at least one biologically active agent, wherein said solution forms an encapsulation layer around said biological agent.

10. (Withdrawn) The solution of claim 9, wherein said biological agent is a drug or pharmaceutical agent

11. (Original) A bioactive glass composite, comprising:
a biocompatible polymer,
a bioactive glass including at least one calcium, and at least one phosphorous molecular species

12. (Original) The composite of claim 11, wherein said composite is in the form of microfibers, said fibers having a diameter less than 100 μm .

13. (Original) The composite of claim 11, wherein said composite is in the form of particles, microspheres, or coatings.

14 (Original) The composite of claim 12, wherein cells when seeded proliferate on said fibers.

15. (Original) The composition of claim 14, wherein said cells are stem cells.

16. (Original) The composition of claim 15, wherein said stem cells proliferate in the absence of any growth hormones

17. (Original) The composition of claim 12, wherein said fibers are substantially equally spaced to form an organized scaffold.

(WP325900:1)

18. (Original) The composition of claim 17, wherein said equal spacing is less than 50 μm .

19 (Original) The composition of claim 17, wherein said equal spacing is less than 25 μm .

20. (Original) The composition of claim 11, wherein a porosity of said composition is at least 50%.

21. (Original) The composition of claim 11, further comprising at least one biologically active agent.

22 (Original) The composition of claim 21, wherein said composition forms an encapsulation layer around said biological agent.

23 (Original) The composition of claim 21, wherein said biologically active agent is adsorbed onto the surface of said composition or chemically attached to a surface of said composition.

24. (Original) The composition of claim 22, wherein said encapsulated biologically active agent is in the form of at least one selected from the group consisting of microcapsules, microspheres, microparticles, microfibers, sol gel matrices, and reinforcing fibers.

25. (Original) The composition of claim 22, wherein said encapsulation layer is continuous, wherein a sustained release profile of said biologically active agent is provided.

26. (Original) The composition of claim 11, further comprising at least one protein.

27 (Original) The composition of claim 26, wherein said protein comprises at least one selected from the group consisting of collagen (including cross-linked collagen), fibronectin,

laminin, elastin (including cross-linked elastin), osteonectin, bone sialoproteins (Bsp), alpha-2HS-glycoproteins, bone Gla-protein (Bgp), matrix Gla-protein, bone phosphoglycoprotein, bone phosphoprotein, bone proteoglycan, protolipids, bone morphogenetic protein, cartilage induction factor, platelet derived growth factor and skeletal growth factor

28. (Original) The composition of claim 11, wherein said composition is disposed on a surface of or integrated within a medical device adapted for implantation into a patient.

29. (Original) The composition of claim 28, wherein said medical device is a prosthetic device.

30. (Original) A method of repairing hard or soft tissue defects, comprising the steps of:
applying a fiber composition comprising a biocompatible polymer, a bioactive glass including at least one calcium and at least one phosphorous molecular species to a defect site on a patient

31. (Original) The method of claim 30, wherein said composition is in the form of microfibers, said fibers having a diameter less than 100 μm .

32. (Original) The method of claim 30, wherein said fibers are substantially equally spaced to form an organized scaffold.

33. (Original) The method of claim 30, wherein said equal spacing is less than 50 μm .

34. (Original) The method of claim 30, where said composition is in the form of particles.

35. (Original) The method of claim 30, wherein cells proliferate on or around said composition in the absence of any growth hormones.

36. (Original) A method of forming a bioactive glass, comprising the steps of:

{WP325900.1}

mixing a biocompatible polymer, a gelable inorganic base material, and
at least one calcium and phosphorous molecular species, and
hydrolizing said mixture.

37. (Original) The method of claim 36, further comprising the step of forming a plurality of fibers, wherein said forming process is at a temperature of no more than 200 C

38. (Original) The method of claim 37, wherein said forming step comprises air-spraying or extruding